

**Amendment to the Claims:**

*This listing of claims replaces all prior versions, and listings, of claims in the application.*

**Listing of Claims:**

1. (Currently Amended) A method of making a fluorinated precursor of a superconducting ceramic wherein the precursor is not superconducting, said method comprises:

- a) providing a solution comprising a rare earth salt, an alkaline earth metal salt and a copper salt;
- b) spraying said solution onto a substrate to provide a precursor-covered substrate; and
- c) heating said precursor-covered substrate in an atmosphere containing fluorinated gas to provide said fluorinated precursor wherein the precursor is not superconducting.

2. (Original) A method according to Claim 1 wherein said solution has a pH in the range of approximately 1 to 5.

3. (Original) A method according to Claim 1 further comprising dispersing said solution in a carrier gas before spraying said solution on said substrate, wherein said carrier gas comprises an inert gas.

4. (Original) A method according to Claim 3 wherein said inert gas is selected from the group consisting of nitrogen, argon, helium and mixtures thereof.

5. (Original) A method according to Claim 3 wherein said carrier gas further comprises oxygen.

6. (Original) A method according to Claim 1 further comprising heating said substrate before spraying said solution on said substrate.

7. (Original) A method according to Claim 1 wherein said rare earth salt is selected from the group consisting of a yttrium (Y) salt, a neodymium (Nd) salt, a, a ytterbium (Yb) salt, an europium (Eu) salt, a gadolinium (Gd) salt, a dysprosium (Dy) salt, a holmium (Ho) salt, an erbium (Er) salt, a lanthanum (La) salt, a lutetium (Lu) salt, a samarium (Sm) salt, a thulium (Tm) salt, and mixtures thereof.

8. (Original) A method according to Claim 6 wherein said rare earth salt is a yttrium (Y) salt.

9. (Original) A method according to Claim 7 wherein said rare earth salt is selected from the group consisting of a rare earth nitrate, a rare earth acetate and mixtures thereof.

10. (Original) A method according to Claim 7 wherein said rare earth salt is selected from the group consisting of a rare earth sulfate, a rare earth chloride, a rare earth bicarbonate and mixtures thereof.

11. (Previously Presented) A method according to Claim 1 wherein said salt of an alkaline earth metal is selected from the group consisting of a strontium (Sr) salt and a barium (Ba) salt and mixtures thereof.

12. (Original) A method according to Claim 11 wherein said salt of an alkaline earth metal is a barium (Ba) salt.

13. (Original) A method according to Claim 12 wherein said barium (Ba) salt is selected from the group consisting of a barium nitrate, a barium acetate and mixtures thereof.

14. (Original) A method according to Claim 12 wherein said barium salt is selected from the group consisting of a barium sulfate, a barium chloride and mixtures thereof.

15. (Original) A method according to Claim 1 wherein said copper salt is selected from the group consisting of a copper nitrate, a copper acetate and mixtures thereof.

16. (Original) A method according to Claim 1 wherein said copper salt is selected from the group consisting of a copper sulfate, a copper sulfide, a copper chloride and mixtures thereof.

17. (Original) A method according to Claim 1 wherein said substrate is selected from the group consisting of a single crystalline ceramic, polycrystalline ceramic, a single crystal and a metal.

18. (Original) A method according to Claim 17 wherein said substrate is selected from the group consisting of  $\text{SrTiO}_3$ ,  $\text{LaAlO}_3$ , zirconia,  $\text{CeO}_2$ ,  $\text{Y}_2\text{O}_3$ ,  $\text{MgO}$ , and  $\text{SrRuO}_3$ .

19. (Original) A method according to Claim 17 further comprising placing a buffer layer on said metal substrate before spraying said solution.

20. (Original) A method according to Claim 1 wherein said fluorinated gas is selected from the group consisting of  $\text{CHF}_3$ ,  $\text{CH}_2\text{F}_2$ ,  $\text{CH}_3\text{F}$ ,  $\text{CHF}_2\text{CHF}_2$  (HFC 134),  $\text{CHF}_2\text{CF}_3$  (HFC 125),  $\text{CHF}_2\text{CH}_3$  (HFC 152a),  $\text{CF}_3\text{CH}_2\text{F}$  (HFC 134a),  $\text{CH}_3\text{CF}_3$ ,  $\text{CH}_2\text{FCH}_3$ ,  $\text{CHF}_2\text{CH}_2\text{F}$ ,  $\text{CH}_2\text{FCH}_2\text{F}$ ,  $\text{CF}_3\text{CH}_2\text{CF}_3$  (HFC 236fa), a fluorinated propane, a fluorinated propylene, a fluorinated ethylene and mixtures thereof.

21. (Original) A method according to Claim 1 wherein said fluorinated gas comprises  $\text{CF}_3\text{CH}_2\text{F}$  (HFC 134a).

22. (Original) A method according to Claim 1 wherein said solution comprises Y, Ba and Cu in a ratio of 1:2:0.5.

23. (Original) A method according to Claim 1 further comprising subjecting said solution to a high voltage Corona discharge before or during the spraying of said solution on said substrate.

24. (Original) A method according to Claim 23 wherein said solution comprises Y, Ba and Cu in a ratio of 1:2:3.5.

25. (Original) A method according to Claim 1 where said atmosphere containing fluorinated gas is subject to a high voltage electrical discharge.

26. (Original) A method according to Claim 1 further comprising transforming the fluorinated precursor into a crystalline superconducting ceramic.

Claims 27-56 (Cancelled).

57. (Original) A method of inhibiting the conversion of a fluorinated precursor film into a crystalline film, wherein the film comprises rare earth metal, alkaline earth metal cuprate, said the method comprising adding a small amount of fluorinated gas during a heat treatment process by which a precursor film is to be converted into a crystalline film.

58. (Original) A method according to Claim 57 wherein the fluorinated gas is added at a pressure of approximately 10 milliTorr or greater during said heat treatment process.